



ZARIN ROOY CASPIAN

Technical Datasheet

Zinc Dust Superfine ZRC-24

Our Zinc Dust is extensively used in the manufacturing of industrial coatings and complies with ISO 3549

Properties	Unit	Typical value	Limit	Test Method
Particle size d (0.5)	µm	3.5	3-4	Laser diffraction technique
Sieve Residue (32 µm)	% max	0.01	<0.1	ISO 3549
Total Zinc	% min	99.0	>98.0	ISO 3549
Metallic Zinc	% min	96.0	>94.0	ISO 3549
Lead (Pb)	% max	0.02	<0.2	ISO 3549
Cadmium (Cd)	% max	0.002	<0.1	ISO 3549
Iron (Fe)	% max	0.003	<0.05	ISO 3549
Arsenic (As)	% max	0.0001	<0.0005	ISO 3549
Chloride (Cl)	% max	0.001	<0.005	ISO 3549
Acid-insoluble	% max	0.02	<0.05	ISO 3549
Color	Bluish gray			Visual
shape	spherical			SEM Technique
Specific gravity	7.0 – 7.2			ISO 787/10

The information contained herein has been compiled to the best of Zarin Rooy Caspian's knowledge and is presented without any obligation.

Applications:

- Painting
- Plating
- Chemical Process
- Purification

Packaging:

- Paper bags 25kg
- Metal drums 25-50 kg
- Big bags 250-1000 kg

Storage:

Indoor in a dry ventilated location. To maximize the shelf life and maintain product integrity, do not open the packaging until the material is to be used

Head Office:

Address: No.126, West Sarv Blvd, Saadat Abad, Tehran, Iran

Phone: (+98)2125902000

Fax: (+98)2122362410

Email: info@zrczinc.com

Website: www.zrczinc.com



ISO 9001-ISO 14001-ISO45001